

TECHNICAL DATE SHEET

ALFAPRO

BASE MATERIAL: Polylactic acid

PROPERTIES

PROPERTIES	VALUE	METOD AND CONDICTION	
PHYSICAL & MECHANICAL	Density	1,24 g/cm ³	ISO 1183
	CHARPY (test 80x10x4 mm)	14 kJ/m ²	ISO 179-1eU
	Elongation at break: - Untreated	2,90%	ISO 527
	- Annealed	ND	ISO 527
	Tensile strength at break:		
	- Untreated	30 Mpa	ISO 527
	- Annealed	ND	ISO 527
	Flexure Modulus: - Untreated	2750 Mpa	ISO 527
	- Annealed	ND	ISO 527
	THERMAL	Heat Deflection Temperature	
- Untreated		58 °C	ISO 75
- Annealed		116 °C	ISO 75

SUGGESTED PRINTER SETTING

	VALUE	UNIT
Extruder Temperature	210 - 230	°C
Print Speed	40 - 120	mm/s
Bed Material	0 - 50	°C
Annealing Temperature	100 ° C for 30-60 min	suggested in sand and/or with support

PRODUCT DETAILS & CERTIFICATION

Diameter	1,75 mm 2,85 mm	Tolerance ± 0,05mm Tolerance ± 0,10mm
----------	--------------------	--

The information supplied in relation to our products recommendations or otherwise, is collected from source considered to be dependable or internally developed. Ciceri de Mondel Srl assumes no liability and makes no warranties of any kind about the accuracy of this datas. The user assumes all responsibility for the use of all information provided